

## Lega metallo /Tungsten Alloy

### Caratteristiche fisico/chimiche

DATA SHEET

OD17.5D

Typical Applications:	Dynamic Balancing
Ref.cod	ASTM B777-07 Class 2
Nominal Composition:	93% W – 4.9% Ni – 2.1% Fe
Density:	17.5gm/cm <sup>3</sup>
Hardness:	26 HRC
Elongation:	7%
Ultimate Tensile Strength	700 N/mm <sup>2</sup>
Magnetic Properties:	Weakly Ferro Magnetic