

Lega metallo /Tungsten Alloy

Caratteristiche fisico/chimiche

DATA SHEET

OD18

Typical Applications:	Radiation Shielding Static Balancing
Nominal Composition:	95% W – 3.5% Ni – 1.5% Cu
Density:	18 gm/cm ³
Hardness:	27 HRC
Elongation:	0,07
Ultimate Tensile Strength	680 N/mm ²
Magnetic Properties:	Non Magnetic