

## Lega metallo /Tungsten Alloy

### Caratteristiche fisico/chimiche

DATA SHEET

OD18.5

|                           |                           |
|---------------------------|---------------------------|
| Typical Applications:     | Ballast & Balancing       |
| Ref.cod                   | ASTM B777-07 Class 4      |
| Nominal Composition:      | 97% W – 2.1% Ni – 0.9% Fe |
| Density:                  | 18,5gm/cm <sup>3</sup>    |
| Hardness:                 | 28 HRC                    |
| Elongation:               | 5%                        |
| Ultimate Tensile Strength | 880 N/mm <sup>2</sup>     |
| Magnetic Properties:      | Weakly Ferro Magnetic     |